



Proppant 30/70 Technical Data Sheet

Frac Sand
 Product name: 30/70
 Magnolia Frac Sand, LLC
 693 Hwy. 61 North
 Natchez, Mississippi 39120
 Contact: Paul C. Miller
 Tel: (817) 994-6600
 Email: pmiller.magnoliafrac@blain-co.com

Proppant 30/70 Physical Properties

	7000	8000
Crush resistance	9.6%	14.1%

K Value: 7K

	30	35	40	45	50	60	70
US Standard Sieve N	0.1%	11.5%	24.9%	26.0%	18.2%	13.8%	5.2%

In-Size:	99.6%	Specific Gravity:	2.66
Mean Diameter:	0.39 mm	Sphericity:	0.6
Median Diameter:	0.378 mm	Roundness:	0.7
Bulk Density:	1.48 g/cc	Acid Solubility in HCl:	1.4%

www.MagnoliaFracSand.com

DATA FROM:
 PropTester Inc. Reports
 RFA# 101-19-06-97-16-B

