



Proppant 20/40 Technical Data Sheet

Frac Sand
 Product name: 20/40
 Magnolia Frac Sand, LLC
 693 Hwy. 61 North
 Natchez, Mississippi 39120
 Contact: Paul C. Miller
 Tel: (817) 994-6600
 Email: pmiller.magnoliafrac@blain-co.com

Proppant 20/40 Physical Properties

	4000	5000
Crush resistance	9.9%	18.1%

K Value: 4K

	20	25	30	35	40	45
US Standard Sieve Number	0.1%	15.2%	15.8%	30.6%	29.2%	9.1%

In-Size:	90.7%	Specific Gravity:	91.7 lb ft³
Mean Diameter:	0.562 mm	Sphericity:	0.8
Median Diameter:	0.548 mm	Roundness:	0.6
Bulk Density:	1.47 g/cc	Acid Solubility in HCl:	1.0%

www.magnoliafracsand.com

DATA FROM:
 Stim-Lab Reports
 RFA# SL8113, SL9760 and SL10918

