



Proppant 30/50 Technical Data Sheet

Frac Sand
 Product name: 30/50
 Magnolia Frac Sand, LLC
 693 Hwy. 61 North
 Natchez, Mississippi 39120
 Contact: Paul C. Miller
 Tel: (817) 994-6600
 Email: pmiller.magnoliafrac@blain-co.com

Proppant 30/50 Physical Properties

	6000	7000
Crush resistance	8.9%	11.5%

K Value: 6K

	30	35	40	45	50	70
US Standard Sieve Number	2.7%	38.2%	38.4%	12.0%	4.7%	3.5%

In-Size:	93.3%	Specific Gravity:	2.66
Mean Diameter:	0.476 mm	Sphericity:	0.6
Median Diameter:	0.463 mm	Roundness:	0.7
Bulk Density:	1.48 g/cc	Acid Solubility in HCl:	0.4%

www.MagnoliaFracSand.com

DATA FROM:
 PropTester Inc. Reports
 RFA# 101-19-06-97-16-B

