



## Proppant 40/70 Technical Data Sheet

Frac Sand

Product name: 40/70

Magnolia Frac Sand, LLC

693 Hwy. 61 North

Natchez, Mississippi 39120

Contact: Paul C. Miller

Tel: (817) 994-6600

Email: pmiller.magnoliafrac@blain-co.com

### Proppant 40/70 Physical Properties

	6000	7000
Crush resistance	8.4%	13.0%

K Value: 6K

	40	45	50	60	70	100
US Standard Sieve Number	0.5%	20.8%	43.2%	26.7%	8.0%	0.7%

In-Size: 98.7%  
 Mean Diameter: 0.318 mm  
 Median Diameter: 0.313 mm  
 Bulk Density: 1.45 g/cc

Specific Gravity: 2.66  
 Sphericity: 0.6  
 Roundness: 0.7  
 Acid Solubility in HCl: 1.1%

[www.MagnoliaFracSand.com](http://www.MagnoliaFracSand.com)

DATA FROM:  
 PropTester Inc. Reports  
 RFA# 101-19-06-97-16-B

